

| Grades | pH | Viscosity (mPa·s/25°C) | Non-volatile (%) | MFT (°C) | Film properties | | | | |
|--------|------|---------------------------|---------------------|-------------|-----------------|------------------|--------------------|-------------------|-----------------|
| | | | | | Hardness | Water resistance | Barrier properties | Darkness of print | Heat resistance |
| B-1000 | 8~10 | ≦1000 | 20 | ≦5 | H | ○ | ◎ | ○ | ◎ |
| B-1500 | 8~10 | ≦1000 | 20 | ≦5 | H | ◎~○ | ◎~○ | ◎~○ | ○ |
| B-2000 | 8~10 | ≦1000 | 20 | ≦5 | H | ◎ | ◎ | ◎ | ○ |
| B-3000 | 8~10 | ≦3000 | 20 | ≦5 | H | ◎ | ◎ | ◎ | ○ |
| B-4100 | 7~9 | ≦500 | 37 | ≦5 | H | ◎ | ○ | ◎ | ○ |