

AURUM™ PL450C, PD450

Thermoplastic Polyimide

AURUM™ PL450C and PD450 are a thermoplastic polyamide of Tg=245°C, Tm=388°C.

PD450 powder, PL450C : granule

General Properties	Typical value	Unit	Test method
Specific gravity	1.33	-	ASTM D792
MFR, 400°C-1.05kgf	8	g/10min	ASTM D1238
Mold shrinkage (MD/TD)	0.7 / 0.8	%	Mitsui chemical method

Mechanical Properties	Typical value	Unit	Test method
Tensile strength	90	MPa	ASTM D638
Elongation at brake	90	%	ASTM D638
Flexural strength	140	MPa	ASTM D790
Flexural modulus	3	GPa	ASTM D790
Izod impact strength	90	J/m	ASTM D256

Thermal properties	Typical value	Unit	Test method
HDT	230	°C	ASTM D648
CLTE (MD/TD)	5.5 / 5.5	10 ⁻⁵ /°C	ASTM D696

AURUM™ PL450C, PD450

Thermoplastic Polyimide

Injection molding condition

Drying temperature	200	°C
Drying time	> 5	h
Temperature setting	80	°C
Cylinder 1	390-400	°C
Cylinder 2	400-410	°C
Cylinder 3	400-410	°C
Nozzle Temperature	400-410	°C
Mold Temperature	180-200	°C