

TAFMER™ M Series

Grades	MFR (190°C) g/10min (*1)	MFR (230°C) g/10min (*1)	Density kg/m ³ (*2)	FDA conformity	EU directive
MA8510	2.4	5.0	885	Not Conforming	Conforming(*3)
MH7010	0.9	1.8	870	Not Conforming	Conforming(*3)
MH7020	0.7	1.5	870	Not Conforming	Conforming(*3)
MA9015	11	23	896	Not Conforming	Conforming(*3)
MH5020C	0.6	1.2	866	Not Conforming	Conforming(*3)

(*1) ASTM D1238

(*2) ASTM D1505

(*3) EU Directive

All the monomers and additives used in the above TAFMER™ grade are listed in the EU Directive 2002/72/EC and its amendment 2008/39/EC.

The only additives with Specific Migration Limit (SML) are: Furan-2,5-dione(CAS No. 108-31-6, Ref No. 19960)

: SML(T) = 30 mg/kg expressed as maleic acid

n-Octadecyl 3,5-di-t-butyl-4-hydroxy hydrocinnamate (CAS No.2082-79-3, Ref No.68320)

: SML= 6 mg/kg

Please ensure that the SML and Overall Migration (OM) are within the specified value in the end-use products.

In case the regulatory information you are looking for is not covered by our standard certificate, please contact us.

Information contained herein is based on the material, information and data available as of the end of December 2011. No warranty is given for any data or evaluation results contained herein. It is also assumed that the product is to be used under normal conditions and with due precautions. If the product is to be used in any special manner, the user is requested safety measures to meet such new use or application.