

## AURUM® JNF3020

- FEATURES

Non Reinforced/Filled, Wear Resistance

- TYPICAL PROPERTIES

ITEM	TEST METHOD	UNIT	VALUE	
<b>Physical Properties</b>				
S.G.	ASTM D 792	—	1.43	
Mold Shrinkage (MD/TD)	MCI 法	%	0.77/1.20	
<b>Mechanical Properties</b>				
Tensile Strength	ASTM D 638	MPa	65	
Tensile Elongation	ASTM D 638	%	10	
Flexural Strength	ASTM D 790	MPa	100	
Flexural Modulus	ASTM D 790	GPa	2.4	
IZOD Impact Strength	ASTM D 256	J/m	82	
<b>Thermal Properties</b>				
H.D.T. @ 1.82MPa	ASTM D 648	°C	224	
C.L.T.E. (MD/TD)	ASTM D 696	10 <sup>-5</sup> /K	N.D.	